



# NORIS SALOREX UNI HSSE

## Katalog-Nr. 6642 / 7642




vaporisiert


Schaft h9



3xD



Form C



Form E

<b>A</b>	$\leq 1100\text{N/mm}^2$	6-15 m/min	Emulsion
<b>R</b>	$\leq 850\text{N/mm}^2$	6-8 m/min	Emulsion / Öl



# NORIS SALOREX UNI HSSE

## Katalog-Nr. 6642 / 7642



TIN Beschichtung

Schaft h9



3xD



Form C

<b>A</b>	$\leq 1100\text{N/mm}^2$	8-18 m/min	Emulsion
<b>R</b>	$\leq 850\text{N/mm}^2$	8-10 m/min	Emulsion / Öl
<b>F</b>	GJL, GJS, GJV, GTW, GTS	10-20 m/min	Emulsion
<b>N</b>	G-AlMg, GD-AlSi, CuZn, CuAl	6-15 m/min	Emulsion



# NORIS SALOREX UNI HSSE

## Katalog-Nr. 6642 / 7642




TICN Beschichtung

Schaft h9



3xD



<b>A</b>	$\leq 1100\text{N/mm}^2$	8-18 m/min	Emulsion
<b>R</b>	$\leq 850\text{N/mm}^2$	8-10 m/min	Emulsion / Öl
<b>F</b>	GJL, GJS, GJV, GTW, GTS	10-20 m/min	Emulsion
<b>N</b>	G-AlMg, GD-AlSi, CuZn, CuAl	6-15 m/min	Emulsion